

PA 3200 GF

PA12-GB

EOS GmbH - Electro Optical Systems

Product Texts
Product Texts

PA 3200 GF is a whitish, glass-filled polyamide 12 powder, which is characterised by an excellent stiffness in combination with good elongation at break. Laser-sintered parts made from PA 3200 GF possess excellent material properties:

- high stiffness
- high mechanical wear-resistance
- good thermal loadability
- excellent surface quality
- high dimensional accuracy and detail resolution
- good processability
- excellent long-term constant behaviour

A typical application for PA 3200 GF is the usage e.g. for final parts within the engine area of cars, for deep-drawing dies or any other application which requires particular stiffness, high heat distortion temperature and low abrasive wear.

Mechanical properties	Value	Unit	Test Standard
Izod Impact notched (23°C)	4.2	kJ/m	ISO 180/1A
Izod Impact unnotched (23°C)	21	kJ/m	ISO 180/1U
Shore D hardness (15s)	80	-	ISO 868
Ball indentation hardness	98	MPa	ISO 2039-1

3D Data	Value	Unit	Test Standard
---------	-------	------	---------------

The properties of parts manufactured using additive manufacturing technology (e.g. laser sintering, stereolithography, Fused Deposition Modelling, 3D printing) are, due to their layer-by-layer production, to some extent direction dependent. This has to be considered when designing the part and defining the build orientation.

Tensile Modulus (X Direction)	3200	MPa	ISO 527-1/-2
Tensile Modulus (Y Direction)	3200	MPa	ISO 527-1/-2
Tensile Modulus (Z Direction)	2500	MPa	ISO 527-1/-2
Tensile Strength (X Direction)	51	MPa	ISO 527-1/-2
Tensile Strength (Y Direction)	51	MPa	ISO 527-1/-2
Tensile Strength (Z Direction)	47	MPa	ISO 527-1/-2
Strain at break (X Direction)	9	%	ISO 527-1/-2
Strain at break (Y Direction)	9	%	ISO 527-1/-2
Strain at break (Z Direction)	5.5	%	ISO 527-1/-2
Charpy impact strength (+23°C, X Direction)	35	kJ/m	ISO 179/1eU
Charpy notched impact strength (+23°C, X Direction)	5.4	kJ/m	ISO 179/1eA
Flexural Modulus (23°C, X Direction)	2900	MPa	ISO 178
Flexural Strength (X Direction)	73	MPa	ISO 178
Temp. of deflection under load (1.80 MPa, X Direction)	96	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa, X Direction)	157	°C	ISO 75-1/-2

Thermal properties	Value	Unit	Test Standard
Melting temperature (20°C/min)	176	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 10N)	179	°C	ISO 306
Vicat softening temperature (50°C/h 50N)	166	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density (lasersintered)	1220	kg/m	EOS Method

Powder colour (ac. to safety data sheet)

White

-

-

Characteristics

Processing

Laser Sintering, Rapid Prototyping

Features

Low Coefficient of Friction